



LONDON METAL EXCHANGE

Special Contract Rules for Standard Lead

Quality: Lead and Lead Alloys – Lead
BS EN 12659:1999 (Material No. PB970R)

Element	Composition in %	
Indicative Lead Content	99.970	
Ag	0.0050	maximum
As	0.0010	maximum
Bi	0.030	maximum
Cd	0.0010	maximum
Cu	0.0030	maximum
Ni	0.0010	maximum
Sb	0.0010	maximum
Sn	0.0010	maximum
Zn	0.0005	maximum
Total	0.030	maximum

Note: Indicative Lead Content: 100 minus total of impurities

4 November 2008