



LONDON METAL EXCHANGE

Special Contract Rules for Tin

Quality: Tin and Tin Alloys – Ingot Tin
BS EN 610:1996 (Grade Designation 99.85)

Element	Composition in %	
Sn	99.85	minimum
Al	0.0010	maximum
As	0.030	maximum
Bi	0.030	maximum
Cd	0.0010	maximum
Cu	0.050	maximum
Fe	0.010	maximum
Pb	0.050	maximum
Sb	0.050	maximum
Zn	0.0010	maximum
Total of all impurities	0.150	maximum

4th November 2008